



STANDARD CORROSION TEST RESULTS

Finish	Test	Standard Results	Protocol
Black/Gray Phosphate	Salt Spray Results	ASTM B117	24 hours, no red rust
Yellow Zinc	Salt Spray Results	ASTM B117	48 hours, no red rust
Clear Zinc	Salt Spray Results	ASTM B117	24 hours, no red rust
Dracrotized	Salt Spray Results	ASTM B117	500 hours, no red rust
GrabberGard	Salt Spray Results	ASTM B117	1,000 hours, no red rust
GrabberGard	Kesternich Results	DIN 50018, 2.0L	15 cycles, no red rust
304 Stainless Steel	Salt Spray Results	ASTM B117	1000 hours, no red rust
316 Stainless Steel	Salt Spray Results	ASTM B117	1500 hours, no red rust

All Grabber corrosive coatings listed:

Meet or exceed the corrosion resistance criterion as described in ASTM B633-98. Section 7.4

Type III 12 hours

When testing is performed as outlined in ASTM B117 "Practice for operating Salt Spray (Fog) Apparatus"